DATA SHEET

FULBAT FPC12-26 CYCLIC BAT

www.fulbat.com - 😯 FULBAT




NON-SPILLABLE




FPC Series are deep cycle batteries specially designed for long duration cyclic applications, ie with use in charge and then intensive discharge. With advanced AGM valve regulated technology and oversized negative plates, the FPC Series ensure very good cyclic performance with greater depth of discharge for mobility-type applications such as medical, golf and also renewable energies storage. In harsh use conditions (high temperature, higher deep of discharge...), the Gel FPG range is recommended.

DIMENSIONS & WEIGHT





TERMINAL (MM)



SPECIFICATION									
Nominal voltage	12V (6 cells)								
Nominal capacity	26Ah (20hr)								
Cycle life	Up to 400 cycles at 80% DDD* (80% capacity - 20°C) Up to 500 cycles at 50% DDD* (80% capacity - 20°C)								
Internal resistance	Approx 13mΩ								
Terminal	T12								
Max. discharge current	360A (5 sec)								
Reference capacity	26.0Ah (20hr, 1.80V/cell, 25°C/77°F) 24.0Ah (10hr, 1.80V/cell, 25°C/77°F) 21.1Ah (5hr, 1.75V/cell, 25°C/77°F) 19.1Ah (3hr, 1.75V/cell, 25°C/77°F) 15.5Ah (1hr, 1.60V/cell, 25°C/77°F)								
Charge voltage									
Standby use voltage	13.5V ~ 13.8V 25°C/77°F Temperature compensation: -20mV/°C/Cell								
Cycle use voltage	14.4V ~ 15.0V 25°C/77°F Temperature compensation: -20mV/°C/Cell								
Operating temp. range	Discharge: -15°C ~ 50°C Charge: 0°C ~ 40°C Storage: -15°C ~ 40°C								
Nominal operating temp. range	25°C ± 3°C / 77°F ± 5°F								
Self discharge	Can be stored for up to 6 months at 25°C/77°F and then recharging is recommended. Monthly self-discharge ratio is less than 3% at 25°C/77°F								
Capacity affected by temp.	40°C/104°F 103% 25°C/77°F 100% 0°C/32°F 86%								
Container material	A.B.S. UL94-HB								
	*DDD = Depth of discharge								

APPLICATIONS Mohility **Golf Caddy** Leisure Marine Wind

APPROVALS

ISO9001 - Quality management system ISO14001 - Environnmental management System Approved for transport by Air (IATA)



DATA SHEET

FULBAT FPC12-26 CYCLIC BATT

www.fulbat.com - 🕶 FULBAT


CONSTANT CURRENT DISCHARGE (AMPERES) AT 25°C/77°F

F.V/Time	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	35.1	29.6	25.8	18.6	14.8	12.0	7.44	5.80	4.70	3.82	3.33	2.72	2.27	1.27
1.80V/cell	44.9	35.7	30.5	21.9	17.2	13.4	8.12	6.24	5.02	4.10	3.57	2.88	2.40	1.29
1.75V/cell	49.3	39.0	32.9	22.8	17.8	14.0	8.43	6.36	5.13	4.21	3.67	2.93	2.42	1.30
1.70V/cell	53.8	41.7	34.5	23.7	18.5	14.5	8.76	6.54	5.27	4.32	3.75	2.98	2.45	1.32
1.65V/cell	58.0	44.3	36.7	25.0	19.0	15.0	9.00	6.82	5.45	4.44	3.83	3.02	2.50	1.34
1.60V/cell	63.0	47.4	39.1	26.4	19.8	15.5	9.31	7.02	5.62	4.58	3.91	3.05	2.52	1.35


CONSTANT POWER DISCHARGE (WATTS/CELL) AT 25°C/77°F

F.V/Time	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	65.6	55.7	49.2	35.7	28.6	23.3	14.5	11.3	9.21	7.50	6.58	5.38	4.49	2.55
1.80V/cell	82.7	66.3	57.3	41.6	33.0	25.9	15.7	12.1	9.78	8.03	7.03	5.70	4.75	2.57
1.75V/cell	89.7	71.8	61.1	43.0	34.0	27.0	16.3	12.3	10.0	8.23	7.22	5.79	4.79	2.59
1.70V/cell	96.4	76.1	63.9	44.6	35.3	27.8	16.9	12.6	10.2	8.41	7.36	5.87	4.84	2.64
1.65V/cell	103.3	80.4	67.6	46.8	36.0	28.6	17.3	13.2	10.6	8.64	7.51	5.96	4.93	2.67
1.60V/cell	110.2	84.9	71.2	49.0	37.2	29.4	17.8	13.5	10.8	8.88	7.65	6.01	4.98	2.68


DISCHARGE CHARACTERISTICS




TEMPERATURE EFFECTS IN RELATION TO BATTERY CAPACITY




SELF DISCHARGE CHARACTERISTICS



CHARGING CHARACTERISTICS (CYCLE USE)



CYCLE LIFE IN RELATION TO DEPTH OS DISCHARGE



No supplementary charge required (carry out supplementary charge before use if 100% capacity is required)

- Supplementary charge required before use. Optional charging way as below: 1.Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell 2. Charged for above 20 hours at limited current 0.25CA and constant voltage 2.45V/cell 3. Charged for 8-10 hours at limited current 0.05CA

80

40

C Supplementary charge may often fail to recover the capacity. The battery should never be left standing till this is reached



Α

В